

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 398 587
A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 90305044.1

(51) Int. Cl.⁵: H01L 23/31

(22) Date of filing: 10.05.90

(30) Priority: 19.05.89 GB 8911607

(43) Date of publication of application:
22.11.90 Bulletin 90/47(54) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IT LI LU NL SE(71) Applicant: THORN EMI plc
4 Tenterden Street
London W1A 2AY(GB)

(72) Inventor: Whalley, Peter David
23 Fairfields, Great Kingshill
Buckinghamshire, HP15 6EP(GB)
Inventor: Evans, Stephen Daniel
181 Ashford Avenue
Hayes, Middlesex, UB4 0ND(GB)
Inventor: Shaw, John Edward Andrew
45 Colne Avenue
West Drayton, Middlesex, UB7 7AL(GB)

(74) Representative: Hurst, Richard Arthur
Alexander et al
THORN EMI Patents Limited The Quadrangle
Westmount Centre Uxbridge Road
Hayes Middlesex UB4 0HB(GB)

(54) A method of encapsulation for devices and devices encapsulated.

(57) A capillary fill encapsulation technique and a device so encapsulated is described such that a

selected region of a device may be encapsulated whilst leaving other regions of the device uncovered.




FIG. 1

EP 0 398 587 A2

The present invention relates to a method of encapsulating devices and has particular, though not exclusive, relevance to electronic devices.

A difficulty exists in reliably and accurately encapsulating devices in a manner which lends itself to high volume production, especially where one or more areas of the device must be left uncovered by the encapsulant material. This is the case, for example, where the device in question includes an ion-selective field effect transistor (ISFET) of the kind having its gate region treated to render it selective of a chosen constituent of a fluid under test. In these circumstances, the gate region of the ISFET must remain capable of exposure to the fluid in question whilst other regions of the device need to be encapsulated.

Although the devices in question are typically electronic semi-conductive devices, the invention is also applicable to microelectronic devices such as microengineered structures and small screen printed devices, and small-scale optical devices such as optical-fibre connectors.

An object of this invention is to provide a method whereby a selected region of a device may be reliably and accurately encapsulated whilst leaving at least one other region of the device uncovered by the encapsulant material, and another object is to provide devices that are so selectively encapsulated.

According to the invention there is provided a method of applying a liquid encapsulant to a first region of a device but not to a second region of said device, the method comprising the steps of:

(a) defining a passageway along which said encapsulant can be drawn by capillary action, said passageway being bounded in part by said first region of said device, along which said encapsulant can be drawn by capillary action, and in part by a cover member overlying said device and formed with an aperture, substantially registering with said second region, of dimensions sufficient to inhibit said capillary action at said second region.

(b) introducing said encapsulant into said passageway so as to cover said first region whilst leaving said second region uncovered due to said inhibition of said capillary action, and

(c) allowing or causing said encapsulant to cure to render said encapsulant material substantially immobile in relation to said device.

The invention also encompasses devices encapsulated in accordance with the foregoing method.

In order that the invention may be clearly understood and readily carried into effect, some embodiments thereof will now be described, by way of example only, with reference to the accompanying drawings of which:

Figure 1 shows, in cross-sectional view, a

semiconductor device and some associated components prior to encapsulation by a method in accordance with one example of the invention;

Figure 2 shows, in view similar to Figure 1, a subsequent step in the method;

Figure 3 shows, in plan view, the device of Figure 2 at the same step in the method;

Figure 4 shows, in similar view to Figures 1 and 2, the encapsulating stage of the method; and

Figures 5, 6, 7 and 8 show, in similar views to Figures 1, 2 and 4, alternative methods in accordance with other examples of the invention.

European Patent Application No. 883061863 (publication No. 0300641) describes a process by which two components can be joined together by the use of a porous gasket, to which is added a liquid adhesive. Capillary action ensures a complete and uniform distribution of the adhesive throughout the porous gasket, guaranteeing a firm bond of defined geometry after the adhesive dries. The present invention describes a process whereby a low-to-moderate viscosity encapsulant is drawn into a narrow space by capillary action to cover and protect metallic interconnects whilst leaving the chemically sensitive regions of the chip uncontaminated and able subsequently to be exposed to solution.

Figure 1 shows an ISFET 1 mounted on a substrate 2 and wire bonded as at 3, 4 in a conventional manner to conductive tracks 5, 6 formed on the substrate 2 in a known manner. A spacer 7 of a thickness slightly greater than the ISFET chip 1 surrounds the chip except for a small opening 8, Figure 3, which is left to allow the later introduction of the encapsulant. A sheet 9 of transparent material (conveniently a thin sheet of polyester about 30 m) with a hole 10 through the sheet 9 of lateral dimension slightly larger than that of the sensitive region 11 on the chip 1 is located with the hole 10 over the chemically sensitive region 11 of the chip 1. An arrangement as shown in Figure 2 is then obtained. A plan view is represented in Figure 3.

The spacer 7 by holding the sheet 10 to 200 m above the chip 1, prevents the bond wires 3, 4 from being pressed down sufficiently to contact the edge of the chip 1 as this may result in a short-circuit. This can be achieved by locating the chip 1 in a depression or hole 12 in a solid substrate 2' - (e.g. alumina) or in flexible substrates (polyimide sheet) as indicated by Figure 5. The bond wire 3 or 4 and the ball formed in the wire bonding process may contact and support the thin sheet material 9 as long as distortion of the wires 3, 4 does not lead to contact faults. A further possibility is shown in Figure 6, whereby the chip 1 is mounted as before on a planar substrate 2 and is surmounted by a flow cell cap 13 (used to introduce the solution

under test to the chemically sensitive gate region of the ISFET) which incorporates a spacer component 14 to prevent bond wire 3, 4 damage and an opening (not shown) to allow the encapsulant to be introduced. Such a flow cell cap 13 can be readily mass produced by a technique such as injection moulding.

In Figures 2, 3, 4 and 6 the spacers 7 used to prevent the bond wires 3, 4 being excessively depressed are positioned beyond the edges of the chip 1. Alternatively, or additionally spacers 7 may, with advantage be positioned between the chip 1 and the overlying perforated sheet 9. These spacers may either be attached to the chip 1 or be attached to, or form part of, the overlying sheet.

The technique of introducing the encapsulant is common to all methods. A liquid encapsulant (e.g. a uv cross-linkable material) can be placed at the edge of the chip 1 and capillary action pulls the encapsulant over the chip 1 except where the hole 10 opening exists in the sheet 9 over the chemically sensitive region 11. The entire object can then be exposed to uv radiation resulting in cross-linking of the polymer (as shown in Figure 4). To reduce the possibility of hydrostatic pressure forcing encapsulant over the chip 1 and on to the chemically sensitive region 11 through the addition of surplus encapsulant material, the process may be conducted with the substrate 2, and chip 1 and perforated sheet 9, held at an angle such that hydrostatic pressure does not act to cause encapsulant to flood the sensitive area 11. The invention is not predicated on the use of uv-curing encapsulants, and the capillary fill method of introducing and defining the encapsulant may utilise materials cured by visible or other radiation, and indeed may employ encapsulants which are not radiation cured e.g. two part epoxy compositions or silicone rubber sealant preparations. Use of non radiation curing encapsulants does however impose greater constraints on the dimensions of the structures used and the viscosity of the encapsulant.

The use of the invention is compatible with other terms of bonding e.g. tape automatic bonding (TAB) and flip-chip bonding as well as conventional wire bonding. Moreover, the region to be left exposed on the chip 1 (chemically sensitive region) can be precisely defined prior to the application of the encapsulant, by defining the size and shape of the hole 10 in the cover sheet 9, and furthermore, the use of a flow cell cap (as shown in Figure 6) enables several manufacturing steps to be combined.

Figure 7 shows an arrangement where material formed on the chip 1 provides a spacer 15. The material may be in the form of, for example, posts. Such structures are formed from photolithographic

techniques on wafers of ISFET devices using suitable thick film photoresist material.

Arrangements where the spacer structure 15 forms part of the perforated sheet or the component overlying the chip are shown in Figures 8 and 9 respectively.

Furthermore, it will be appreciated that the spacer structures 7, 14, 15 utilised to prevent the band wires 3, 4 from being forced into contact with the chip 1 need not only be in the form of posts, but may be isolated ridges, and/or a ridge surrounding the hole 10 which is to be positioned over the chemically sensitive 11 area of the device.

Although photolithographic or screen printing processes may be used to form such spacer structures 7, 14, 15, they may be more conveniently formed by embossing or moulding techniques.

The embossed or moulded structures 7, 14, 15 may be formed in the sheet material before, after or simultaneously with the hole 10 formation; or may be formed as part of the moulding of components such as flow caps.

It will be appreciated by those skilled in the art that the use of sheets or other components bearing spacer structures 7, 14, 15 to overlie the ISFET chip 1 requires that before they are brought into contact, the alignment of overlying components and the chip 1 be carried out at a sufficient separation to avoid damage to the band wires 3, 4 by the spacer structures 7, 14, 15.

It will further be appreciated by those skilled in the art that a method in accordance with the present invention is not restricted in its application to that of solely electronic devices. The method is equally well applicable to technologies such as optical coupling which may require certain regions to be covered by an encapsulant, but other regions to be free from the encapsulant. Indeed, the invention herebefore described is versatile enough to be applicable to technologies of which the inventor is not aware.

Claims

1. A method of applying a liquid encapsulant to a first region of a device but not to a second region of the device, the method comprising the steps of;

(a) defining a passageway along which the encapsulant may be drawn by capillary action, the passageway being bounded in part by the first region of the device and in part by a cover member overlying the device, which cover member is formed with an aperture, substantially registering with the second region, of dimensions sufficient to inhibit capillary action at the second region;

(b) introducing the encapsulant into the passageway so as to completely cover the first region

with the encapsulant whilst leaving the second region free from the encapsulant due to the inhibition of the capillary action.

2. A method according to Claim 1 wherein the encapsulant material is allowed or caused to be rendered immobile in relation to the device. 5

3. A method according to Claim 2 wherein the encapsulant material is rendered immobile by exposure to light of a predetermined wavelength.

4. A method according to Claim 3 wherein the light is ultra violet light. 10

5. A device produced by the methods described in Claim 1.

6. A device, the device comprising a first region and a second region, the first region completely covered by an encapsulant material, and the second region being free from the encapsulant material. 15

7. A device according to Claim 5 comprising a chip, a substrate and an optically transparent cover member; the chip being mounted on the substrate and underlying the cover member, the cover member being held remote from both the chip and the substrate. 20

8. A device according to Claim 7 wherein support structures for holding the cover member remote from both the chip and the substrate are formed by photolithography. 25

9. A device according to Claims 5, 6, 7 and 8 wherein the chip is an ion-selective field effect transistor. 30

35

40

45

50

55




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 398 587 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 90305044.1

(51) Int. Cl.5: **H01L 23/31**

(22) Date of filing: 10.05.90

(30) Priority: 19.05.89 GB 8911607

(43) Date of publication of application:
22.11.90 Bulletin 90/47(54) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IT LI LU NL SE(68) Date of deferred publication of the search report:
02.01.91 Bulletin 91/01(71) Applicant: THORN EMI plc
4 Tenterden Street
London W1A 2AY(GB)


(72) Inventor: Whalley, Peter David
23 Fairfields, Great Kingshill
Buckinghamshire, HP15 6EP(GB)
Inventor: Evans, Stephen Daniel
181 Ashford Avenue
Hayes, Middlesex, UB4 0ND(GB)
Inventor: Shaw, John Edward Andrew
45 Colne Avenue
West Drayton, Middlesex, UB7 7AL(GB)

(74) Representative: Hurst, Richard Arthur
Alexander et al
THORN EMI Patents Limited The Quadrangle
Westmount Centre Uxbridge Road
Hayes Middlesex UB4 0HB(GB)

(54) A method of encapsulation for devices and devices encapsulated.

(57) A capillary fill encapsulation technique and a device so encapsulated is described such that a

selected region of a device may be encapsulated whilst leaving other regions of the device uncovered.

**FIG. 4**



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 90 30 5044

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	EP-A-0 193 251 (CORNING GLASS WORKS) " column 6, lines 9 - 57; figures 1, 7 " - - -	1-6,9	H 01 L 23/31
A,D	EP-A-0 300 641 (THORN EMI) " the whole document " - - - - -	1,2,5,9	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			H 01 L
The present search report has been drawn up for all claims			
Place of search		Date of completion of search	Examiner
The Hague		08 November 90	DELPORTE B.P.M.
<div>CATEGORY OF CITED DOCUMENTS</div> <div><div>X: particularly relevant if taken alone</div><div>Y: particularly relevant if combined with another document of the same category</div><div>A: technological background</div><div>O: non-written disclosure</div><div>P: intermediate document</div><div>T: theory or principle underlying the invention</div></div> <div><div>E: earlier patent document, but published on, or after the filing date</div><div>D: document cited in the application</div><div>L: document cited for other reasons</div><div>&: member of the same patent family, corresponding document</div></div>			